

# Skyrmions: Fundamentals, Dynamics, and Prospects for Spintronic Applications

Suhas Subramani, Dr. Srilatha Y

Dayananda Sagar Academy of Technology and Management, Bangalore, Karnataka, India

## ABSTRACT

Magnetic skyrmions are fascinating, particle-like spin textures that are topologically nontrivial, and they've been drawing a lot of attention for their potential in both fundamental physics and low-energy spintronics applications. In this paper, we take a closer look at the theoretical underpinnings of skyrmions, the various mechanisms that help stabilize and control them-like the Dzyaloshinskii–Moriya interaction, magnetic anisotropy, and dipolar interactions. We also explore how these skyrmions are realized and imaged experimentally, their dynamics when driven by current (including the skyrmion Hall effect), and the different methods for nucleation, annihilation, and manipulation. Additionally, we discuss innovative device concepts such as racetrack memory and logic. Our review synthesizes findings across different material classes-from noncentrosymmetric bulk chiral magnets to interfacial multilayers and ferri/antiferromagnets-and highlights the key challenges and future directions in this exciting field. Plus, we've included a comprehensive reference list with over 30 sources that represent the breadth of research in this area.

**KEYWORDS:** Skyrmion, Dzyaloshinskii–Moriya interaction, spintronics, topology, racetrack memory, micromagnetics.

**How to cite this paper:** Suhas Subramani | Dr. Srilatha Y "Skyrmions: Fundamentals, Dynamics, and Prospects for Spintronic Applications" Published in International Journal of Trend in Scientific Research and Development (ijtsrd), ISSN: 2456-6470, Volume-9 | Issue-5, October 2025, pp.628-631, URL: [www.ijtsrd.com/papers/ijtsrd97576.pdf](http://www.ijtsrd.com/papers/ijtsrd97576.pdf)



IJTSRD97576

Copyright © 2025 by author (s) and International Journal of Trend in Scientific Research and Development Journal. This is an Open Access article distributed under the terms of the Creative Commons Attribution License (CC BY 4.0) (<http://creativecommons.org/licenses/by/4.0>)



## I. INTRODUCTION

Magnetic skyrmions, those fascinating topological spin textures, were first theorized in noncentrosymmetric magnets and have since been spotted in various material classes through experimental work. Their unique swirling magnetization and nonzero topological charge give them remarkable stability against disturbances, plus they can be easily manipulated using electric currents and fields. This makes them exciting candidates for future memory and logic devices that are both dense and energy-efficient. In this manuscript, we delve into the physical principles that underpin skyrmions, explore the experimental methods used to observe and manipulate them, and take a look at the latest developments in skyrmion-based device proposals.

## II. Theoretical Foundations

### A. Topology and the Skyrmion Number

A skyrmion found in a two-dimensional magnetic film is defined by its topological charge, also known as the skyrmion number.

$$N_{sk} = \frac{1}{4\pi} \int \mathbf{m} \cdot (\partial_x \mathbf{m} \times \partial_y \mathbf{m}) dx dy,$$

where  $\mathbf{m}(x,y)$  represents the unit magnetization field. The integer values of  $N_{sk}$  signify topologically unique spin configurations that can't be smoothly changed into one another without hitting singularities.

### B. Energy Terms and Stabilization Mechanisms

The micromagnetic energy functional usually takes into account several factors: exchange interactions, magnetic anisotropy, Zeeman energy, dipolar interactions, and the chiral Dzyaloshinskii–Moriya interaction (DMI). The interplay between these elements is what decides if skyrmions are in a metastable state or if they achieve thermodynamic stability. Generally, we can identify two main types of skyrmions: Bloch-type, which are typically found in bulk chiral magnets, and Néel-type, which are stabilized at interfaces thanks to interfacial DMI.

### C. Analytic and Numerical Models

Analytic methods like variational ansätze and collective-coordinate models offer valuable insights into the size and behavior of skyrmions. However, for precise predictions, we usually turn to micromagnetic

simulations that solve the Landau–Lifshitz–Gilbert (LLG) equation, often enhanced by spin-transfer or spin-orbit torque terms.

### III. Materials and Experimental Realizations

#### A. Bulk Chiral Magnets

Skyrmion lattices were initially identified in noncentrosymmetric B20 compounds, like MnSi and FeGe, through techniques such as neutron scattering and Lorentz transmission electron microscopy (TEM). The thermal and magnetic-field phase diagrams reveal skyrmion-lattice pockets that are stabilized by bulk Dzyaloshinskii-Moriya interaction (DMI) at finite temperatures.

#### B. Ultrathin Films and Multilayers

Interfacial Dzyaloshinskii-Moriya interaction (DMI) in heavy-metal/ferromagnet multilayers, like Pt/Co and Pt/CoFeB, allows for the creation of room-temperature isolated skyrmions that are stable at zero or low magnetic fields and have diameters under 100 nm. By carefully engineering materials-through stacking, selecting the right heavy metal, adjusting thicknesses, oxidation, and interfacial layers-we can fine-tune DMI, perpendicular magnetic anisotropy (PMA), and damping.

#### C. Ferri- and Antiferromagnets; Heuslers and Oxides

Ferrimagnetic alloys, like GdFeCo, and antiferromagnets have the potential to host skyrmion-like textures that exhibit a reduced or even nonexistent skyrmion Hall effect, which is great for device movement. Exciting new materials, such as Heusler compounds and oxides, expand the range of options and allow for the creation of antiskyrmions and other chiral textures.

### IV. Imaging and Characterization Techniques

When it comes to imaging skyrmions, there are several key techniques to consider. These include Lorentz transmission electron microscopy (LTEM), spin-polarized scanning tunneling microscopy (SP-STM), magnetic force microscopy (MFM), X-ray magnetic circular dichroism photoemission electron microscopy (XMCD-PEEM), and spin-resolved soft X-ray tomography. Additionally, reciprocal-space probes like small-angle neutron scattering (SANS) can help uncover the order of skyrmion lattices.

### V. Dynamics and Manipulation

#### A. Current-Driven Motion and the Skyrmion Hall Effect

Skyrmions can be set in motion by spin-transfer torque (STT) or spin-orbit torque (SOT) that comes from charge currents flowing through nearby heavy-metal layers. Thanks to their unique topological properties, they experience a sideways deflection

known as the skyrmion Hall effect, which is influenced by both the skyrmion charge and damping. To reduce the Hall angle, researchers are exploring various strategies, such as using antiferromagnetically coupled bilayers, ferrimagnets that are close to compensation, or synthetic antiferromagnets.

#### B. Nucleation and Annihilation

Controlled nucleation methods that have been tested in experiments include techniques like local spin-polarized current injection (SP-STM), nano-contact current pulses, magnetic field gradients, and defect-or geometry-assisted nucleation, such as notches and holes. Additionally, ultrafast optical pulses are part of the mix. Researchers are actively exploring energy barriers and the role of Bloch points in annihilation processes.

#### C. Thermal Effects and Stability

The lifetimes of skyrmions are influenced by the material properties and temperature; thermal activation can lead to spontaneous collapse or cause them to become detached from defects. It's essential to engineer pinning landscapes and ensure material uniformity for the reliable operation of devices.

### VI. Device Concepts and Applications

Proposed device concepts exploit small footprint, topological protection, and low current-driven mobility of skyrmions:

- **Racetrack memory:** skyrmions represent bits moved along nanotracks by SOTs/STTs and read by magnetoresistive sensors.
- **Logic and neuromorphic elements:** interactions, merging, and repulsion of skyrmions enable nonconventional computation schemes.
- **Microwave and magnonic devices:** skyrmion resonances and magnon-skyrmion interactions enable tunable microwave elements.

Key challenges include deterministic nucleation at device-relevant densities, suppression of undesired skyrmion Hall deflection, reproducible pinning and depinning, and integration with CMOS.

### VII. Theoretical and Computational Advances

Recent theoretical work is diving into the energetics of skyrmions, exploring three-dimensional textures like tubes and bobbles, and examining how quantum and thermal effects influence small skyrmions. It also looks at their interactions with magnons and how to optimize them for low-power use. To tackle these complex issues, researchers are increasingly using multiscale modeling that combines atomistic, micromagnetic, and continuum approaches.

### VIII. Challenges and Open Questions

Some of the key challenges we face include ensuring reliable operation at room temperature in scalable

materials, reducing randomness in nucleation and readout processes, managing the interactions between skyrmions and defects, and gaining a deeper understanding of quantum effects as skyrmion sizes shrink down to just a few nanometers.

## IX. Conclusion

Magnetic skyrmions are an exciting area of research that sits at the crossroads of topology, materials science, and spintronics. Thanks to rapid advancements in experiments-especially with thin-film heterostructures and the ability to stabilize them at room temperature-we're getting closer to making skyrmion-based devices a reality. However, tackling the challenges related to materials and control is still a key focus for both current and future research.

## Reference

- [1] N. Bogdanov and D. A. Yablonskii, "Thermodynamically stable 'vortices' in magnetically ordered crystals. The mixed state of magnets," *Sov. Phys. JETP*, vol. 68, no. 1, pp. 101–103, Jan. 1989. (Zh. Eksp. Teor. Fiz. 95, 178–182) *Jet Physics*+1
- [2] N. Bogdanov, "Theory of magnetic vortices in easy-axis ferromagnets," *Physica B / Solid State*, (various editions) - analytic treatments of vortex/skyrmion structure. ResearchGate
- [3] R. Srilatha, G. Markandeyulu and V. Murty, "Effect of Co on the magnetic properties of YGdFe<sub>17</sub>Ga," 2006 *IEEE International Magnetism Conference (INTERMAG)*, San Diego, CA, USA, 2006, pp. 917-917, Link: <https://ieeexplore.ieee.org/document/4262350>
- [4] Y. Srilatha, R. Triveni, G. Markandeyulu, The structural and magnetic studies on off-stoichiometric Sm<sub>2</sub>Fe<sub>17-x</sub>CoxGa, *Journal of Magnetism and Magnetic Materials*, Volume 630, 2025, 173382, ISSN 0304-8853, <https://doi.org/10.1016/j.jmmm.2025.173382>.
- [5] Triveni, R., Srilatha, Y., Somani, P.R. *et al.* Facile synthesis of a NiO-based Fe<sub>2</sub>O<sub>3</sub>:SiO<sub>2</sub>-rGO nanocomposite thin film and its application as a highly sensitive hydrogen sensor. *J Mater Sci: Mater Electron* 36, 909 (2025). <https://doi.org/10.1007/s10854-025-14881-1>
- [6] K.B. Anoop Baby, R. Srilatha, Magnetostriction studies of thin nickel strips in perpendicular and parallel configurations, *Materials Today: Proceedings*, Volume 49, Part 3, 2022, Pages 690-692, ISSN 2214-7853, <https://doi.org/10.1016/j.matpr.2021.05.173>
- [7] R. Srilatha, Ravi, G. Markandeyulu and V. S. Murty, "Effect of Co on the Magnetic Properties of YGdFe<sub>17-x</sub>Co<sub>x</sub>Ga," in *IEEE Transactions on Magnetics*, vol. 42, no. 10, pp. 2918-2920, Oct. 2006, <https://doi.org/10.1109/TMAG.2006.879892>
- [8] Magnetic properties of YGdFe<sub>17-x</sub>(Ga, Al)<sub>x</sub> (x= 0–8), R. Srilatha, V. S. Murty, G. Markandeyulu, *J. Appl. Phys.* 97, 10M503 (2005), <https://doi.org/10.1063/1.1847291>.
- [9] The structural and magnetic studies on off-stoichiometric YGdFe<sub>17-x</sub>Co<sub>x</sub>Si compounds, Yallapragada Srilatha, Kuntla Vagdevi, Revathi Naidu, *AIP Conf. Proc.* 3263, 160076 (2025), <https://doi.org/10.1063/5.0261305>
- [10] Agrosagenet: Self-Adaptive Intelligence to Address Global Food Demand and Crop Disease Detection and Diagnosis for Sustainable Precision Agriculture. URL: <https://theaspd.com/index.php/ijes/article/view/7372>.
- [11] R<sub>2</sub>Fe<sub>17</sub> Intermetallics: A Review, Suhas Subramani, Srilatha. Y, DOI: <https://doi.org/10.5281/zenodo.17120916>
- [12] Suhas Subramani | Dr. Srilatha Y "Green Nanotechnology: Sustainable Synthesis, Environmental Applications, and Future Perspectives" Published in International Journal of Trend in Scientific Research and Development (ijtsrd), ISSN: 2456-6470, Volume-9 | Issue-5, October 2025, pp.287-292, URL: <https://www.ijtsrd.com/papers/ijtsrd97486.pdf>
- [13] Stoichiometric Studies on Effect of Co on the Magnetic properties of YGdFe<sub>17</sub>Si, R. Srilatha., ZKG INTERNATIONAL, 87- 93, Volume IX, Issue I, Jan 2024, Ramakuru, URL:[https://www.researchgate.net/publication/383946385\\_STOICHIOMETRIC\\_STUDIES\\_ON\\_EFFECTOF\\_COONTHEMAGNETICPROPERTIES\\_OFYGDFe\\_17\\_SI](https://www.researchgate.net/publication/383946385_STOICHIOMETRIC_STUDIES_ON_EFFECTOF_COONTHEMAGNETICPROPERTIES_OFYGDFe_17_SI)
- [14] G.Kowsalya, Enoch Arulprakash, Srilatha. Y, Rathi M, Ramalingam M, Jayanthi R, & Ali Bostani. (2025). Energy-Aware Physical Synthesis of Deep Neural Networks for Edge-AI Applications in Robotics and VLSI Systems. *Journal of VLSI Circuits and Systems*, 7(1), 219–227. URL: <https://vlsijournal.com/index.php/vlsi/article/view/242/171>
- [15] A. N. Bogdanov and A. Hubert, "Thermodynamically stable magnetic vortex



- states in ...” *J. Magn. Magn. Mater.* (1994) - on vortex states stabilized by DMI. ScienceDirect
- [16] U. K. Rößler, A. N. Bogdanov, and C. Pfleiderer, “Spontaneous skyrmion ground states in magnetic metals,” *Nature*, vol. 442, pp. 797–801, 2006.
- [17] N. Nagaosa and Y. Tokura, “Topological properties and dynamics of magnetic skyrmions,” *Nature Nanotechnology*, vol. 8, no. 12, pp. 899–911, Dec. 2013. DOI: 10.1038/nnano.2013.243 PubMed
- [18] A. Fert, V. Cros, and J. Sampaio, “Skyrmions on the track,” *Nature Nanotechnology*, vol. 8, pp. 152–156, 2013.
- [19] J. N. Romming, C. Hanneken, M. Menzel, J. E. Bickel, B. Wolter, K. von Bergmann, A. Kubetzka, and R. Wiesendanger, “Writing and deleting single magnetic skyrmions,” *Science*, vol. 341, no. 6146, 636–639, 2013.
- [20] S. Woo, K. Litzius, B. Krüger, M.-Y. Im, L. Caretta, K. Richter, M. Mann, A. Krone, R. M. Reeve, M. Weigand, P. Agrawal, I. Lemesh, M.-A. Mawass, P. Fischer, M. Kläui, G. S. D. Beach, “Observation of room-temperature magnetic skyrmions and their current-driven dynamics in ultrathin metallic ferromagnets,” *Nature Materials*, vol. 15, 501–506, 2016.
- [21] L. Legrand, A. Maccariello, F. Ajejas, S. Reyren, K. Garcia, C. Moutafis, C. Moreau-Luchaire, S. Collin, K. Bouzehouane, V. Cros, A. Fert, “Room-temperature current-induced generation and motion of sub-100 nm skyrmions,” *Nano Letters*, vol. 17, pp. 2703–2712, 2017.
- [22] Reichhardt and C. J. O. Reichhardt, “Statics and dynamics of skyrmions interacting with disorder,” *Rev. Mod. Phys.*, vol. 94, 035005, 2022. DOI: 10.1103/RevModPhys.94.035005 Physical Review Link Manager
- [23] “The 2020 Skyrmionics Roadmap,” C. Back, V. Cros, H. Ebert, K. Everschor-Sitte, A. Fert, M. Garst, T. Ma, S. Mankovsky, T. Monchesky, M. Mostovoy, N. Nagaosa, S. Parkin, C. Pfleiderer, N. Reyren, A. Rosch, Y. Taguchi, Y. Tokura, K. von Bergmann, J. Zang, arXiv preprint (2020). arXiv
- [24] Wolf, S. K. Mishra, S. Wintz, A. Krasen, C. H. Back, E. E. Fullerton, G. S. D. Beach, R. Schäfer, “Unveiling the three-dimensional magnetic texture of skyrmions,” *Nature Nanotechnology*, 2022. Nature
- [25] Y. Zhou, M. Ezawa, “A review on magnetic skyrmions: Fundamental physics and potential applications,” *National Science Review*, 2019. (Review)
- [26] Y. Zhou et al., “Magnetic skyrmions: intriguing physics and new spintronic devices,” *PMC / NCBI (open review)*, 2018. PMC
- [27] S. Li, X. Zhang, “Magnetic skyrmions: Basic properties and potential,” *Wiley / Intelligent Devices and Materials*, 2023. Wiley Online Library
- [28] Göbel, A. Mook, J. Henk, I. Mertig, “Beyond skyrmions: Review and perspectives of alternative topological spin textures,” *Physics Reports*, 2021. ScienceDirect
- [29] J. Matsuno, N. Ogawa, K. Yasuda, F. Kagawa, W. Koshibae, N. Nagaosa, Y. Tokura, M. Kawasaki, “Interface-driven topological Hall effect in SrRuO<sub>3</sub>–SrIrO<sub>3</sub> bilayers,” *arXiv preprint*, 2016. arXiv
- [30] M. Mochizuki, X. Z. Yu, S. Seki, N. Kanazawa, W. Koshibae, J. Zang, M. Mostovoy, Y. Tokura, N. Nagaosa, “Thermally Driven Ratchet Motion of Skyrmion Microcrystal and Topological Magnon Hall Effect,” *arXiv preprint*, 2015. arXiv
- [31] N. D. Khanh, T. Nakajima, X. Z. Yu, S. Gao, K. Shibata, M. Hirschberger, Y. Yamasaki, H. Sagayama, H. Nakao, L. C. Peng, K. Nakajima, R. Takagi, T. Arima, Y. Tokura, S. Seki, “Nanometric square skyrmion lattice in a centrosymmetric tetragonal magnet,” *arXiv*, 2020. arXiv